Product Datasheet

Fibre-reinforced, cementitious levelling compound

UZIN NC 175

Self smoothing, fibre-reinforced and rapid compound for all floor coverings and wood flooring for thicknesses from 3 to 30 mm

MAIN APPLICATION FIELD:

- smoothing and levelling of wooden substrates for the subsequent installation of textile and resilient floor coverings, wood flooring, ceramics and natural stone.

SUITABLE ON / FOR:

- calcium sulphate or cementitious screeds, concrete
- old screeds or concrete, which may contain old compounds and adhesive residues
- existing and new P4 - P7 or OSB 2 - OSB 4 boards, screwed
- existing ceramic and natural stone coverings, terrazzo or similar
- substrates with joints or critical substrates, e.g. precast screeds or screed boards
- wooden floorboards, wood flooring or any other wooden substrates with joints
- warm water underfloor heating systems
- exposure to castor wheels in accordance with DIN EN 12 529 from 3 mm thickness
- suitable for residential, commercial and industrial areas, e.g. hospitals, busy shopping malls, industrial halls, etc.

CE

0761

Uzin Utz SE
Dieselstrasse 3
89079 Ulm

13

01/01/0019.01

EN 13813:2002

Fibre-reinforced cementitious levelling compound for substrates in interior locations

EN 13813: CT-C40-F10

Reaction to fire	A2fl-s1
Release of corrosive substances	CT
Compressive strength	C40
Flexural strength	F10

PRODUCT BENEFITS/FEATURES:

The special advantage of UZIN NC 175 is the high fibre and polymer content. On critical substrates, UZIN NC 175 offers the best adhesion to the substrate as well as highest safety when renovating. For interior use.

- excellent flow characteristics
- can be raked (notch R3)
- very good absorbency
- for thicknesses from 3 mm

TECHNICAL DATA:

Packaging	paper bag
Pack size	25 kg
Shelf life	min. 9
Water quantity	6.0 - 6.5 litres per 25 kg bag
Color	grey
Consumption	approx. 1.6 kg/m²/mm thickness
Ideal application temperature	20 °C
Working time	25 - 35 minutes*
Ready for foot traffic	approx. 2 - 3
Ready for covering	after approx. 6 hours*
Minimum application temperature	10 °C at ground level
Flow spread ring	approx. 145 mm ± 5 mm
Fire reaction	$A2_{fl}$-s1 acc. to DIN EN 13 501-1

*At 20 °C and 65% relative humidity with max. thickness of 3 mm. See "Ready for covering".

GEV-EMICODE EC 1 PLUS very low emission

EPD

LEED® CONTRIBUTING PRODUCT

0736

LEVEL PLUS EFFECT

UZIN | A brand of UZIN UTZ
DE | Uzin Utz SE | Dieselstrasse 3 | 89079 Ulm | Telephone +49 731 4097-0 | Fax +49 731 4097-110 | E-Mail info@uzin.de | Internet www.uzin.de

UZIN NC 175

SUBSTRATE PREPARATION:

The substrate must be sound, load-bearing, dry, free from cracks and free from materials (dirt, oil, grease) that would impair adhesion. Cement and calcium sulphate screeds must be abraded and vacuumed. Test the substrate in accordance with applicable standard or notices and report any deficiencies.

Any adhesion-reducing or unstable layers, e.g. release agents, loose adhesives, compounds, covering or paint residues, etc. must be removed, e.g. by brushing, abrading, grinding or shot-blasting. Thoroughly vacuum loose material and dust. Use a suitable primer from the UZIN Product Guide according to the type and condition of the substrate. Allow any primer that is applied to dry completely.

The datasheets for other used products have to be observed.

APPLICATION:

1. Put 6 - 6.5 litres of cold, clear water into a clean container. Sprinkle in the contents of the bag (25 kg) while mixing vigorously until a smooth and lump-free compound is obtained. Use a mixing device fitted with a UZIN Mixing Paddle.
2. Pour the compound onto the substrate and spread evenly with a smoothing trowel or a screed rake. The flow and surface can be improved by removing air using a spike roller. If possible, apply to the desired thickness in one coat.

CONSUMPTION INFORMATION:

Layer Thickness	Approx. Consumption	Size / Coverage
3 mm	4.8 kg/m²	25 kg / 5.2 m²
5 mm	8.0 kg/m²	25 kg / 3.1 m²
10 mm	16 kg/m²	25 kg / 1.5 m²

READY FOR COVERING:

Planned Top Layer	Layer Thickness	Ready for Covering
Textile and resilient floor coverings (e.g. PVC, linoleum, rubber), ceramics and natural stone	3 mm	approx. 6 hours*
	5 mm	approx. 6 hours*
	10 mm	approx. 24 hours*
	20 mm	approx. 48 hours*
Textile and resilient floor coverings with Sigan 1 or Sigan Elements Plus + Planus	3 mm	approx. 12 hours
Wood flooring	3 mm	approx. 15 hours*
	5 mm	approx. 15 hours*
	10 mm	approx. 24 hours*
	20 mm	approx. 72 hours*

*At 20 °C and 65% relative humidity.

IMPORTANT NOTES:

- A shelf life of 9 months when stored in dry conditions, in the original packaging. The setting and drying times may become longer if the storage time is prolonged. The properties of the cured material are not affected. Carefully and tightly reseal opened packaging and use the contents as quickly as possible.
- Best applied between 15 - 25 °C and relative humidity below 65%. Low temperatures, high humidity, little air circulation, dense substrates and large thickness will delay the setting and drying time. Whilst high temperatures and low humidity, strong air circulation and absorbent substrates will accelerate setting, drying and readiness for covering. In summer, store in cool conditions and use cold water.
- Expansion, movement and perimeter joints in the substrate must be reflected through to the surface. Fit UZIN Foam Expansion Strips to any adjacent, vertical structures to prevent the ingress of the compound into the joints.
- Can be pumped with continuous, forced-action mixer-pumps, e.g. from manufacturers such as m-tec, P.F.T. and others.
- The substructure of wooden floors must be dry to prevent damage due to damp through rotting or mould formation. Adequate ventilation or rear-ventilation must be provided especially when installing impermeable flooring, e.g. by removing the existing expansion strip or by installing special skirting with vent openings.
- Minimum thickness is 3 mm. A rake with notch R3 can be used.
- When applying in several coats, allow the compound to dry completely. Then apply UZIN PE 360 PLUS as a intermediate primer and leave to dry, before applying subsequent coats.
- For thicknesses above 10 mm and on moisture-sensitive substrates, use epoxy primers, such as UZIN PE 460, gritted.
- Use UZIN PE 630 for priming firmly attached floorboards and other substrates with joints.
- On weak, older substrates with several layers of adhesive or levelling compound, the use of fibre-reinforced, gypsum-based levelling compound UZIN NC 115 is preferred.
- For new mastic asphalt screeds thicknesses up to max. 5 mm and for older mastic asphalt screeds, with old layers attached, thicknesses up to max. 3 mm are permissible. For greater thicknesses gypsum-based levelling compounds such as UZIN NC 110, UZIN NC 112 Turbo or UZIN NC 115 should be used.
- Do not use in exterior or wet areas.
- Protect freshly applied areas from draughts, direct sunlight and sources of heat. Cement-based compounds tend to form cracks on soft or tacky substrates. These soft and tacky layers must therefore be removed as much as possible before applying the compound. Leaving such compounds open for too long also promotes such cracking and should therefore be avoided.
- Do not use as a screed or as a wear surface, a surface covering must always be applied.
- UZIN NC 175 has the approval as shipbuilding equipment product by the maritime occupational association “See-Berufsgenossenschaft Hamburg”, module B and module D. Certificates are available upon request. The permissible thickness is 30 mm. USCG-No. for the system is 164.106/EC0736/113.133.

This product is intended exclusively for professional use by qualified commercial users. It must not be supplied to consumers. The above information is based on our experience and careful investigations. The variety of associated materials and different constructions and working conditions cannot be individually checked or influenced by us. The quality of your work depends, therefore, on your own professional judgement and product usage. If in doubt, conduct a small test or obtain technical advice. Observe the installation recommendations of the floor covering manufacturer. The publication of this Product Data Sheet invalidates all previous product information. The respective updated version of this datasheet can be found on our website under www.uzin.com | 09/2026

- Compounds must not enter between insulation and heating pipes because of the risk of corrosion. This applies in particular for heating pipes made from galvanized steel. Insulation may only be cut off after smoothing.
- Follow the generally acknowledged rules of the trade and technology for the installation of wood flooring and floor covering in respective of the applicable national standards (e.g. EN, DIN, OE, SIA, etc.)

SEALS OF QUALITY & ECOLABELS:

- Low chromate content acc. Regulation (EC) No. 1907/2006 (REACH)
- EMICODE EC 1 PLUS / Very low-emission
- European Model EPD
- Suitable for sustainable building certifications according to: DGNB, QNG, BNB, BREEAM, LEED

COMPOSITION:

Special cements, mineral aggregates, redispersible polymers, high-performance liquefiers and additives.

PROTECTION OF THE WORKPLACE AND THE ENVIRONMENT:

Contains cement low in chromate acc. Regulation (EC) No. 1907/ 2006 (REACH). Cement produces strong alkaline on reaction with water. Avoid contact with skin and eyes. In the event of contact, rinse immediately with water. In the event of skin or eye irritation, seek medical advice. Use protective gloves. When mixing wear a protective dust-mask. Product contains fibres based on synthetic polymer microparticles (SPM). Keep container tightly closed. Immediately collect spilled material from damaged containers and reuse or dispose of properly. Basic prerequisites for best possible indoor air quality following floor covering work are conformity to standards of the working conditions, as well as thoroughly dry substrate, primer and smoothing compound.

DISPOSAL:

Where possible, collect product residues and re-use. Product contains synthetic polymer microparticles (SPM). Avoid release to the environment. Do not allow to get into drains, sewers or ground. Empty paper packaging is recyclable. Collect waste product, mix with water, allow to harden, then dispose as Construction Waste.

This product is intended exclusively for professional use by qualified commercial users. It must not be supplied to consumers. The above information is based on our experience and careful investigations. The variety of associated materials and different constructions and working conditions cannot be individually checked or influenced by us. The quality of your work depends, therefore, on your own professional judgement and product usage. If in doubt, conduct a small test or obtain technical advice. Observe the installation recommendations of the floor covering manufacturer. The publication of this Product Data Sheet invalidates all previous product information. The respective updated version of this datasheet can be found on our website under www.uzin.com | 09/2026